
Technical Data Sheet

ASP-2001 AntiSlipPaper

Quality: 100 gr/qm; 2-side coated

Presentation: sheets, rolls (max. width 140 cm)

Tests	units	Value	Tolerances	Normes
Paper Weight	g / m ²	100	+/- 15%	ISO 536
Thickness	µm	140	+/- 10%	ISO 534
COBB 60	g/m ²	10	<i>Indicatives values</i>	ISO 535
Static rubbing ratio (*)	°	45	<i>Mini : 40</i>	NF Q03-083

*Method: test is undertaken on an inclined plane of glass; pressure of the test weight is 16 gr/cm²

Properties: > printable, recyclable, suitable for the contact with food
> the product retains its Anti Slip properties under temperatures between -30°C and +90°C
> All coated paper should be stored under standard and stable hygrometry an temperature Conditins.
Any exess can lead to blocking phenomena and paper deformation.