

## Technical Data Sheet

### ASP-2001 AntiSlipPaper

Quality: 65 gr/qm; 2-side coated

Presentation: sheets, rolls (max. width 140 cm)

TESTS	UNIT	DIRECTION	VALUE	OBSERVATION	TEST REFERENCE
Paper Weight	g/m <sup>2</sup>		65	+ / - 3	NF Q 03 019
Thickness	µm		80	+ / - 10	NF Q 03 016
Burst Resistance	kPa m <sup>2</sup>		4.2	Values  Indicatives	NF Q 03 053
Lengthening	%	LW CW	2.7 7.4		NF Q 03 004
Tensile	m	LW CW	7240 3920		NF Q 03 004
COBB <sub>180</sub>	gr/m <sup>2</sup>		5		NF Q 03 014
Static Rubbing Coef.*	Degrees		55	min. 45	NF Q 03 083

LW = Lengthwise    CW = Crosswise

\*Method: Test is undertaken on a inclined pane of glass; Pressure of the test weight is 16 gr/cm<sup>2</sup>

**Properties:** printable, recyclable

the product retains its Anti Slip properties under temperatures between -30°C and +120°C