

Technical Data Sheet

SIPA-XS 550 Antirutsch-Pappe

Tests	Units	Median Values	Tolerances	Normes
Grammage	g/m ²	550	+/- 10%	ISO 536
Thickness	µm	865	+/- 10%	ISO 534
Burst Index	kPa	1050	<i>Indicatives values</i>	ISO 2758
Stiffness TABER (MD)	g.cm	810	<i>Indicatives values</i>	ISO 2493
(CD)		320		
Tensile Strength (MD)	kN.m	4870	<i>Indicatives values</i>	//
(CD)		1930		
Coefficient of friction			>0.60	VDI 2700 Bl.14

Properties :

- ↻ 100 % recyclable environment-friendly basic material paperboard
- ↻ Printable
- ↻ The product preserves his properties of skid resistance for temperatures ranging between -30°C and 120°C.